



TEXISCREEN PERMATONE CO

Texiscreen Permatone CO is a water-based 100% solvent free textile ink, designed for direct wet-on-wet printing on a wide range of natural and synthetic fabrics. Once heat cured, the unique formula offers an unsurpassed balance of colour brightness, softness and durability to wash, rub and dry-clean, eliminating the need for additives.

Permatone CO also has excellent screen stability allowing exceptional screen open time.

Texiscreen Permatone CO has a matching system which is PANTONE® approved enabling the system to produce simulations of 950 PANTONE® colours. As a water-based product, equipment is easily cleaned with water. After heat fixing, prints exhibit excellent wash, rub and dry-clean resistance.

Important: Stir well before use. Compatibility with all substrates must be checked before commencing a production run .

Main Characteristics

Drying	Thinning & Wash-up	Mesh Range	Stencil Type	Coverage & Mesh No.	Applications	Fabrics	Colour Range
For optimum fastness Permatone CO should be heat cured.	If necessary, thin with up to 5% water. Dried in ink may be washed out with CPS KA or A8 Screenwash.	Mono-filament 43-62T. (110-157tpi) With practice, 120T=305 tpi can be used for wet-on-wet printing	Should be water resistant. Emulsion: Recommend Dirasol 916, KIWO Polypus SRX, ULANO LX-660 or CHROMALINE CP-TEX	15-21m ² /L with 62T mesh. (155tpi mesh) 43-60 sq ft/US gallon	T-Shirts, Flags, Banners, Sports and Fashion Wear, Scarves. Swimwear. Upholstery and Window Furnishings.	Cotton. Cotton/ Polyester blends and most synthetic fabrics. The fastness to wash and dry cleaning on wool may be diminished.	9 Permatone Colours plus Black, White, and Extender Base.



Properties

Matt Finish. White spirit free. Low odour. Intermixable, light fast, non-bleeding colours.
Brilliant transparent shades.
Soft handle. Excellent wash and dry clean resistance. Ironable.

Product Resistance

After heat curing, prints exhibit very good resistance to wet/dry rub.

Drying and Curing

For optimum wash and colour fastness, prints should be fully heat cured. Whilst the below information is a guide, the curing schedule used should be chosen to suit the heat resistance of the fabric being printed. Care must be taken with IR dryers to ensure prints are fully cured. When printing on synthetic blends and fabrics, the lower curing temperature and longer drying time is recommended. If your drying conditions fall outside these recommendations, please contact your local Permatone CO representative for technical assistance.

The following curing guidelines are recommendations for ink deposit temperatures, not dryer temperatures. This should be checked with temperature strips to ensure the appropriate temperatures are achieved.

2-3 Minutes @ 160°C (355°F)

5-6 Minutes @ 140°C (285°F)

8-9 Minutes @ 120°C (250°F)

Fastness

Light Fastness is good. No colours yield less than 6 on the Blue Wool Scale and most are the full 8/8. Fully heat cured prints have excellent wash and dry clean fastness.

Colour Matches: Note that high temperatures combined with strong detergents can cause colour changes in some colour matches. It is therefore imperative that all formulations are checked for acceptable wash fastness properties prior to production.

Rub Resistance

After heat curing, prints exhibit very good resistance to wet/dry rub.

Standard Colours

Permatone CO

- | | |
|---------------------|--------------------|
| CO001 Black | CO132 (s) Violet |
| CO021 White | CO154 (s) Magenta |
| CO046 (s) Yellow RS | CO218 (s) Blue |
| CO057 (s) Yellow GS | CO316 (s) Green |
| CO103 (s) Orange | CO381 (s) Extender |
| CO122 (s) Red YS | |
| CO153 (s) Red BS | |

Available in 1L, 4L and some colours in 15L containers. (s) = Base Colours
CO381 also available in 200L pack size (made to order only)



COLORMAKER INDUSTRIES

44 Orchard Rd, Brookvale NSW 2100

Phone: +61 2 9939 7977

Email: info@permaset.com.au

www.permaset.com.au



Ancillary Products

During printing, fabrics must be held in place by means of a pressure sensitive adhesive so that good definition is obtained and registration maintained. Permaset Table Adhesive is suitable for this purpose.

Safety and Handling

Permatone CO has been formulated to be free of any toxic chemicals. The range does not contain a flash point, and as such exempt from Flammable Liquids regulations. Permatone CO is also free from Lead and other prohibited heavy metals, such as Cadmium and Chromium VI.

Permatone CO also complies with Oekotex Class 2. Comprehensive information on the safety and handling of products in the Permatone CO range of inks and ancillaries is provided in the appropriate Safety Data Sheet (SDS) which is available on request.

Environmental Information

Permatone CO does not contain ozone depleting chemicals such as CFC's and HCFC's. It is also formulated free of aromatic hydrocarbons. Permatone CO is free of any volatile solvent.

Storage

Containers should be kept in a cool place and tightly closed when not in use.
Excess ink from the screen should be disposed of in accordance with local regulatory authorities.

VER 1406

The information and recommendations contained in this Product Information sheet, as well as technical advice otherwise given by representatives of our Business, whether verbally or in writing, are based on our present knowledge and believed to be accurate. However, no guarantee regarding their accuracy is given as we cannot cover or anticipate every possible application of our products and because manufacturing methods, printing stocks and other materials vary. For the same reason our products are sold without warranty and on condition that users shall make their own tests to satisfy themselves that they will fully meet their particular requirements. Our policy of continuous product improvement might make some of the information contained in this Product information sheet out of date and users are requested to ensure that they follow current recommendations.